## **Provisional Technical Datasheet**





# PP - Homopolymer 1030RG for Woven sacks & Monofilament Applications

## **Product Description:**

**PP Homopolymer 1030RG** is a natural colored grade produced by the latest Spheripol II Technology. This Grade is having Exceptional processability with low water carry over, Good balance of tenacity & elongation.

## Applications:

**PP Homopolymer 1030RG** is recommended for stretched tapes of Woven sacks, fabrics for packaging fertilizers, cement, polymers, Food grains & carpet backing. This grade can be used for monofilament / ropes & Leno bags applications.

### **Typical Properties**

Sr. No.	Properties	Test Method	Units	Values*
1	Melt Flow Index ( 230°C & 2.16 kg)	ASTM D1238	g / 10 min	3
2	Tensile Strength @ Yield (50mm / min)	ASTM D638	MPa	33
3	Elongation @ Yield (50mm / min)	ASTM D638	%	8
4	Flexural Modulus	ASTM D790	MPa	1450
5	Notch Izod Impact Strength ( 20°C)	ASTM D256	J/m	40
6	Vicat Softening Point (10N)	ASTM D1525	°C	155
7	Heat Deflection Temperature (0.46N/m2)	ASTM D648	°C	94

<sup>\*</sup> All Mechanical Properties as per ASTM D638 Type I Injection moulded specimen Prepared in accordance with ASTM D 4101

#### **Processing Guidelines:**

1. Barrel Temperature : 220 - 280 °C 2. Die Temperature: 260 - 280 °C 3. Quench Temperature : 30 - 40 °C 4. Stretching Temperature : 155 - 165 °C

#### Regulatory Requirements:

PP Homopolymer 1030RG shall meet the requirements stipulated in IS 10910 on 'Specification for Polypropylene and its Copolymers for safe use in contact with Foodstuff, Pharamaceutical & Drinking water'. The grade and Additives incorporated in this grade shall meet the positive list of constituents as prescribed in IS 10909. The Grade and the additives incorporated in it will also comply with the FDA:CFR Title 21,177.1520, Olefin Polymers

#### Storage & Handling:

Prevent PP Material from direct exposure to sunlight & heat to avoid quality deterioration. The storage location should be dry, dust free and the Storage temperature should not exceed 50°C. Non - compliance to these precautionary measures can lead to degradation of the product causing Color changes, Odor & inadequate product performance.

Disclaimer: IOCL assumes no liability whatsoever in respect of application, processing or any use made of the afore - mentioned information or products, or any consequence thereof. The user undertakes all liability in respect of the application, processing or use of the afore - mentioned information or product, whose quality and other properties he shall verify, or any consequence therof. No liability whatsoever shall attached to any of the IOCL companies for any infringement of the rights owned or controlled by a third party in intellectual, industrial or other property by reason of application, processing or use of the afore-mentioned information or products by the user.

<sup>\*</sup> Typical Values and not to be taken as specifications